



Technical Data Sheet

Durez[®] 12603

phenolic resin

Description:

Durez[®] 12603 is a thermoplastic, oil soluble gum rosin ester with a high melting point. It is supplied in pastil form.

Typical properties:

Test method	Properties	Durez [®] 12603
DCT 1	Appearance	amber pastils
DCT 11C	Melting point clear, °C	133
DCT 292	Acid number 292, mg KOH/g	65
DCT 385	Colour (50/50 resin/cyclohexane), G&H	8

* DCT test methods are available upon request

www.sbhpp.com

SBHPP | HIGH PERFORMANCE PLASTICS BUSINESS UNIT OF SUMITOMO BAKELITE CO., LTD.

SUMITOMO BAKELITE EUROPE N.V. – HENRY FORDLAAN 80 – 3600 GENK - BELGIUM
TEL.: +32 (0)89 320 311 | FAX: +32 (0)89 320 309 | E-MAIL: INFOSBE@SUMIBE.EU

RPR TONGEREN – BTW/VAT / BE 0403 125 169



Technical Data Sheet

Storage:

Durez[®] 12603 is a stable material at ambient temperatures. When stored under optimum storage conditions (below 25°C and 60% relative humidity in unopened original packaging), Durez[®] 12603 has a shelf life of 12 months from the shipping date.

Packaging:

Standard packaging for Durez[®] 12603 is plastic bags, containing 25Kg net. Bags are shipped as 1250Kg unitized pallet loads. All packaging is marked with product number, lot number and net weight.

READ THE MATERIAL SAFETY DATA SHEET BEFORE HANDLING, STORING OR USING THIS PRODUCT.

The information presented herein, while not guaranteed, is to the best of our knowledge true and accurate. No warranty or guarantee express or implied is made regarding the performance or stability of any product, since the manner of use and conditions of storage and handling are beyond our control. No suggestion for product use nor anything contained herein shall be construed as a recommendation for its use in infringement of any existing patent.

www.sbhpp.com

SBHPP | HIGH PERFORMANCE PLASTICS BUSINESS UNIT OF SUMITOMO BAKELITE CO., LTD.

SUMITOMO BAKELITE EUROPE N.V. – HENRY FORDLAAN 80 – 3600 GENK - BELGIUM
TEL.: +32 (0)89 320 311 | FAX: +32 (0)89 320 309 | E-MAIL: INFOSBE@SUMIBE.EU

RPR TONGEREN – BTW/VAT / BE 0403 125 169