



Technical Data Sheet

Durez® 14136 phenolic resin

Description:

Durez® 14136 is a brown liquid, cashew oil modified novolac which requires the addition of hexamethylenetetramine to produce thermosetting properties.

Typical properties:

Test method	Properties	Durez® 14136
DCT 156	Solids content, 135°C, 1g, 1h, %	38
DCT 61	Viscosity at 25°C, cps	2000
DCT 286	Density, g/mL	1,022
DCT 46	pH	9

* DCT test methods are available upon request

www.sbhpp.com

SBHPP | HIGH PERFORMANCE PLASTICS BUSINESS UNIT OF SUMITOMO BAKELITE CO., LTD.

SUMITOMO BAKELITE EUROPE N.V. – HENRY FORDLAAN 80 – 3600 GENK - BELGIUM
TEL.: +32 (0)89 320 311 | FAX: +32 (0)89 320 309 | E-MAIL: INFOSBE@SUMIBE.EU

RPR TONGEREN – BTW/VAT / BE 0403 125 169



Technical Data Sheet

Storage:

Durez[®] 14136 is a stable material at ambient temperatures. When stored under optimum storage conditions (around 20°C and 60% relative humidity in unopened original packaging), Durez[®] 14136 has a shelf life of 6 months from the shipping date.

Packaging:

Standard packaging for Durez[®] 14136 is 220L coated steel drums, containing 200Kg net. All packaging is marked with product number, lot number and net weight.

READ THE MATERIAL SAFETY DATA SHEET BEFORE HANDLING, STORING OR USING THIS PRODUCT.

The information presented herein, while not guaranteed, is to the best of our knowledge true and accurate. No warranty or guarantee express or implied is made regarding the performance or stability of any product, since the manner of use and conditions of storage and handling are beyond our control. No suggestion for product use nor anything contained herein shall be construed as a recommendation for its use in infringement of any existing patent.

www.sbhpp.com

SBHPP | HIGH PERFORMANCE PLASTICS BUSINESS UNIT OF SUMITOMO BAKELITE CO., LTD.

SUMITOMO BAKELITE EUROPE N.V. – HENRY FORDLAAN 80 – 3600 GENK - BELGIUM
TEL.: +32 (0)89 320 311 | FAX: +32 (0)89 320 309 | E-MAIL: INFOSBE@SUMIBE.EU

RPR TONGEREN – BTW/VAT / BE 0403 125 169