

Technical Data Sheet

Durez[®] 19788

phenolic resin

Description:

Durez[®] 19788 is a high melting, very high acid number , thermoplastic polyester type resin, soluble in various solvents including water solutions of ammonia or amines. It is supplied in pastille form.

Typical properties:

Test method	Properties	Durez [®] 19788
DCT 1	Appearance	yellow pastils
DCT 11C	Melting point clear, °C	157
DCT 292	Acid number 292, mg KOH/g	200
DCT 385	Colour, G&H	9

* DCT test methods are available upon request



SBHPP | HIGH PERFORMANCE PLASTICS BUSINESS UNIT OF SUMITOMO BAKELITE CO., LTD.

SUMITOMO BAKELITE EUROPE N.V. – HENRY FORDLAAN 80 – 3600 GENK - BELGIUM TEL.: +32 (0)89 320 311 | FAX: +32 (0)89 320 309 | E-MAIL: INFOSBE@SUMIBE.EU RPR TONGEREN – BTW/VAT / BE 0403 125 169



Technical Data Sheet

Storage:

Durez[®] 19788 is a stable material at ambient temperatures. When stored under optimum storage conditions (below 20°C and 60% relative humidity in unopened original packaging), Durez[®] 19788 will not sinter and has a shelf life of 12 months from the shipping date.

Packaging:

Standard packaging for Durez[®] 19788 is plastic bags, containing 20Kg net. Bags are shipped as 1000Kg unitized pallet loads. All packaging is marked with product number, lot number and net weight.

READ THE MATERIAL SAFETY DATA SHEET BEFORE HANDLING, STORING OR USING THIS PRODUCT.

The information presented herein, while not guaranteed, is to the best of our knowledge true and accurate. No warranty or guarantee express or implied is made regarding the performance or stability of any product, since the manner of use and conditions of storage and handling are beyond our control. No suggestion for product use nor anything contained herein shall be construed as a recommendation for its use in infringement of any existing patent.



SBHPP | HIGH PERFORMANCE PLASTICS BUSINESS UNIT OF SUMITOMO BAKELITE CO., LTD.

SUMITOMO BAKELITE EUROPE N.V. – HENRY FORDLAAN 80 – 3600 GENK - BELGIUM TEL.: +32 (0)89 320 311 | FAX: +32 (0)89 320 309 | E-MAIL: INFOSBE@SUMIBE.EU RPR TONGEREN – BTW/VAT / BE 0403 125 169