



## Technical Data Sheet

---

### **Durez<sup>®</sup> 19900** phenolic resin

#### Description:

Durez<sup>®</sup> 19900 is an oil soluble thermoplastic phenolic resin. It serves as a tackifier for synthetic elastomers used in the manufacturing of tires, belts and hoses. The 19900 resin is recommended for SBR, Butyl, SBR/BR blends and Neoprene rubber based stocks. It is supplied in pastille form.

#### Typical properties:

Test method	Properties	Durez <sup>®</sup> 19900
DCT 104	Softening point (R&B), °C	94
DCT 401	Acid number 401, mg KOH/g	35
DCT 375	Methylol content, %	0,9

\* DCT test methods are available upon request

[www.sbhpp.com](http://www.sbhpp.com)

SBHPP | HIGH PERFORMANCE PLASTICS BUSINESS UNIT OF SUMITOMO BAKELITE CO., LTD.

SUMITOMO BAKELITE EUROPE N.V. – HENRY FORDLAAN 80 – 3600 GENK - BELGIUM  
TEL.: +32 (0)89 320 311 | FAX: +32 (0)89 320 309 | E-MAIL: INFOSBE@SUMIBE.EU

RPR TONGEREN – BTW/VAT / BE 0403 125 169



## Technical Data Sheet

---

### Storage:

Durez<sup>®</sup> 19900 is a stable material at ambient temperatures. When stored under optimum storage conditions ( below 25°C and 60% relative humidity in unopened original packaging ), Durez<sup>®</sup> 19900 has a shelf life of 12 months from the shipping date.

### Packaging:

Standard packaging for Durez<sup>®</sup> 19900 is plastic bags, containing 25Kg net or big bags, containing 500Kg net or big bags containing 1000Kg net. Bags are shipped as 1000Kg unitized pallet loads. All packaging is marked with product number, lot number and net

**READ THE MATERIAL SAFETY DATA SHEET BEFORE HANDLING, STORING OR USING THIS PRODUCT.**

The information presented herein, while not guaranteed, is to the best of our knowledge true and accurate. No warranty or guarantee express or implied is made regarding the performance or stability of any product, since the manner of use and conditions of storage and handling are beyond our control. No suggestion for product use nor anything contained herein shall be construed as a recommendation for its use in infringement of any existing patent.

[www.sbhpp.com](http://www.sbhpp.com)

SBHPP | HIGH PERFORMANCE PLASTICS BUSINESS UNIT OF SUMITOMO BAKELITE CO., LTD.

SUMITOMO BAKELITE EUROPE N.V. – HENRY FORDLAAN 80 – 3600 GENK - BELGIUM  
TEL.: +32 (0)89 320 311 | FAX: +32 (0)89 320 309 | E-MAIL: INFOSBE@SUMIBE.EU

RPR TONGEREN – BTW/VAT / BE 0403 125 169